


CARPENTER LTD  CARPET UNDERLAY	<b>INDIVIDUAL SPECIFICATION SHEET</b>  <b>GLOSSOP PLANT</b>	
Amendment:		Date: 02/10/07
<b>FIRMSTEP</b>		
CHARACTERISTIC	SPECIFICATION	TEST METHOD
ROLL LENGTH	11 m min	
ROLL WIDTH	137cm ± 1%	
DENSITY	145Kg/m <sup>3</sup> ± 5%	
ROLL WEIGHT	16Kg ± 5%	
THICKNESS	7mm ± 5%	
FLAMMABILITY (HOT METAL NUT TEST)	LOW RADIUS of effect	BS 4790:1987 (2003)
THERMAL RESISTANCE	2.3 TOG	BS 4745: 2005
IMPACT SOUND IMPROVEMENT INDEX	36dB	BS EN ISO 140- 8/ BS EN ISO 717-2
DOUBLE STICK CASTOR WHEEL CHAIR TEST	25000+	
CLASSIFICATION	HEAVY CONTRACT USE	BS 5808:1991(2005)
<p><b><u>Disclaimer</u></b>          Whilst ever effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Carpenter has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.          Note: Intrastat No: 3918900090</p>		